

Test acoustique GALERIE RM 1002 Boudoir

ÉLITIS



Fréquence (Hz)	α	TR vide (s)	TR matériau (s)
100	0	12.62	12.65
125	0	11.48	11.75
160	0	12.8	12.87
200	0	11.36	12.51
250	0	12.18	12.21
315	0.02	12.54	11.92
400	0.03	10.73	10.19
500	0.1	10.04	8.52
630	0.13	9.02	7.47
800	0.2	8.14	6.29
1000	0.29	7.27	5.32
1250	0.4	6.85	4.63
1600	0.51	6.48	4.08
2000	0.55	5.87	3.75
2500	0.51	5.03	3.46
3150	0.51	4.21	3.05
4000	0.58	3.44	2.54
5000	0.64	2.79	2.12

Table 1 : GALERIE Boudoir - RM 1002

Coefficient d'absorption et temps de réverbération avec et sans matériau en fonction de la fréquence par bande de tiers d'octave.




Figure 1 : GALERIE Boudoir - RM 1002

Coefficient d'absorption en champ diffus, dispersion et courbe de référence pour le calcul de l'indice unique α_ω

Fréquence (Hz)	α
250	0
500	0.09
1000	0.3
2000	0.52
4000	0.58
α_ω	0.20 (H)

Table 2 : GALERIE Boudoir - RM 1002

Coefficient d'absorption en fonction de la fréquence par bande d'octave et indice unique α_ω

Sound absorption measurements

ÉLITIS

GALERIE RM 1002 Boudoir



Frequency (Hz)	α	TR empty (s)	TR mat (s)
100	0	12.62	12.65
125	0	11.48	11.75
160	0	12.8	12.87
200	0	11.36	12.51
250	0	12.18	12.21
315	0.02	12.54	11.92
400	0.03	10.73	10.19
500	0.1	10.04	8.52
630	0.13	9.02	7.47
800	0.2	8.14	6.29
1000	0.29	7.27	5.32
1250	0.4	6.85	4.63
1600	0.51	6.48	4.08
2000	0.55	5.87	3.75
2500	0.51	5.03	3.46
3150	0.51	4.21	3.05
4000	0.58	3.44	2.54
5000	0.64	2.79	2.12

Table 1 : GALERIE Boudoir - RM 1002

Sound absorption coefficient and reverberation time with and without samples as a function of the frequency in third-octave bands.




Figure 1 : GALERIE Boudoir - RM 1002

Sound absorption coefficient under diffuse field, envelope and reference curve for single-value indicator α_ω

Frequency (Hz)	α
250	0
500	0.09
1000	0.3
2000	0.52
4000	0.58
α_ω	0.20 (H)

Table 2 : GALERIE Boudoir - RM 1002

Sound absorption coefficient as a function of the frequency in octave bands and single-value rating α_ω