

Test acoustique

ÉLITIS

GALERIE RM 1001 Colisée



Fréquence (Hz)	α	TR vide (s)	TR matériau (s)
100	0.01	12.62	12.24
125	0	11.48	11.41
160	0.03	12.8	12.1
200	0	11.36	11.76
250	0.02	12.18	11.7
315	0.05	12.54	11.38
400	0.07	10.73	9.42
500	0.12	10.04	8.3
630	0.17	9.02	7.08
800	0.25	8.14	5.99
1000	0.33	7.27	5.11
1250	0.47	6.85	4.38
1600	0.58	6.48	3.89
2000	0.63	5.87	3.56
2500	0.67	5.03	3.16
3150	0.75	4.21	2.7
4000	0.8	3.44	2.32
5000	0.87	2.79	1.95

Table 1 : GALERIE Colisée- RM 1001

Coefficient d'absorption et temps de réverbération avec et sans matériau en fonction de la fréquence par bande de tiers d'octave.




Figure 1 : GALERIE Colisée- RM 1001

Coefficient d'absorption en champ diffus, dispersion et courbe de référence pour le calcul de l'indice unique α_ω

Fréquence (Hz)	α
250	0.02
500	0.12
1000	0.35
2000	0.63
4000	0.81
α_ω	0.20 (H)

Table 2 : GALERIE Colisée- RM 1001

Coefficient d'absorption en fonction de la fréquence par bande d'octave et indice unique α_ω

Sound absorption measurements

ÉLITIS

GALERIE RM 1001 Colisée



Frequency (Hz)	α	TR empty (s)	TR mat (s)
100	0.01	12.62	12.24
125	0	11.48	11.41
160	0.03	12.8	12.1
200	0	11.36	11.76
250	0.02	12.18	11.7
315	0.05	12.54	11.38
400	0.07	10.73	9.42
500	0.12	10.04	8.3
630	0.17	9.02	7.08
800	0.25	8.14	5.99
1000	0.33	7.27	5.11
1250	0.47	6.85	4.38
1600	0.58	6.48	3.89
2000	0.63	5.87	3.56
2500	0.67	5.03	3.16
3150	0.75	4.21	2.7
4000	0.8	3.44	2.32
5000	0.87	2.79	1.95

Table 1 : GALERIE Colisée- RM 1001

Sound absorption coefficient and reverberation time with and without samples as a function of the frequency in third-octave bands.




Figure 1 : GALERIE Colisée- RM 1001

Sound absorption coefficient under diffuse field, envelope and reference curve for single-value indicator α_ω

Frequency (Hz)	α
250	0.02
500	0.12
1000	0.35
2000	0.63
4000	0.81
α_ω	0.20 (H)

Table 2 : GALERIE Colisée- RM 1001

Sound absorption coefficient as a function of the frequency in octave bands and single-value rating α_ω